


# K HAND COATER

## 30-15-01



▲ **Small K Hand Coater** with clearing/storage rack. Three liquid inks being applied simultaneously. Also shown, Large **K Hand Coater** with a contrast test card.

### MAIN FEATURES

The **K Hand Coater** provides a simple but effective means of applying paints, printing inks, lacquers, adhesives and other surface coatings onto many substrates including paper, board, plastic films, foils, metal plates, glass plates, wood etc. Two or more coatings can be applied side-by-side in a single operation making the system ideal for comparing products.

- Simple, economical
- Will deposit from 4 to 500 micron wet film thickness.
- Good repeatability with special impression bed.
- Stainless steel rods and wire used for K Bars.
- K Bars are numbered and colour coded.
- Two or more products coated simultaneously for comparison

### K101 CONTROL COATER ►

With just a little practice, **K Hand Coaters** produce a uniform and repeatable coating. However, for those users where repeatability is critical (e.g. when used for computer colour matching) or when a number of operators will be carrying out the test work, we have developed the **K Control Coater** illustrated here. This automatic machine (detailed on a separate leaflet) has variable speed and a constant pressure exerted between the bar and substrate.


**Catalog No. 30-01-01**



## K BAR COATING


Wired **K Bars** are produced by winding precision drawn stainless steel wire onto a stainless steel rod resulting in a pattern of identically shaped grooves. These grooves precisely control the wet film thickness. Close wound bars will produce coating thicknesses from 4 to 120µm. Still higher coating weights up to 500µm can be obtained using open wound bars.

### STANDARD K BARS



Close Wound

BAR No.	COLOUR CODE	WIRE DIAMETER		WET FILM DEPOSIT	
		INS	MM	INS	µm
0	White	0.002	0.05	0.00015	4
1	Yellow	0.003	0.08	0.00025	6
2	Red	0.006	0.15	0.0005	12
3	Green	0.012	0.31	0.0010	24
4	Black	0.020	0.51	0.0015	40
5	Horn	0.025	0.64	0.0020	50
6	Orange	0.030	0.76	0.0025	60
7	Brown	0.040	1.00	0.0030	80
8	Blue	0.050	1.27	0.0040	100
9	Tan	0.060	1.50	0.0050	120



Spirally Wound

BAR No.	WIRE DIAMETER		WET FILM DEPOSIT	
	INS	MM	INS	µm
150	0.010	0.25	0.006	150
200	0.014	0.36	0.008	200
300	0.020	0.51	0.012	300
400	0.030	0.76	0.016	400
500	0.040	1.00	0.020	500

Special bars to apply intermediate wet film deposits are manufactured to customer requirements. We stock wire diameters giving the choice of the following deposits (microns) when close wound.

4, 6, 8, 10, 12, 14, 16, 18, 20, 22, 24, 26, 28, 30, 32, 34, 36, 38, 40, 42, 44, 46, 48, 50, 52, 54, 56, 58, 60, 62, 64, 66, 68, 70, 72, 76, 80, 84, 88, 90, 92, 96, 100, 104, 108, 110, 112, 116, 120, 128, 130, 140, 150.

We also manufacture both wired metering bars and plain smoothing bars to fit all laboratory and production width coaters.

## ORDERING

### Small Starter Set

- 1 small impression bed (coating area 11x18cm)
  - 8 short K Bars (specify bar nos)
  - 1 short cleaning/storage rack
  - 500 sheets proofing paper 12x21cm
- Catalog No. 30-15-01**

### Large Starter Set

- 1 large impression bed (coating area 22x34cm)
  - 8 long K Bars (specify bar nos)
  - 1 long cleaning/storage rack
  - 500 sheets proofing paper 18x31cm
- Catalog No. 30-16-01**

**Alternatively, all items can be ordered individually.**

#### Main Headquarters

**Testing Machines Inc.**  
2 Fleetwood Court  
Ronkonkoma, NY 11779  
Tel: (631) 439-5400  
Fax: (631) 439-5420  
Info@testingmachines.com

**Messmer Instruments**  
Unit F1 Imperial  
Business Estate  
West Mill, Gravesend  
Kent DA11 0DL UK  
Tel: +44 (0) 1474 566488  
Fax: +44 (0) 1474 560310

**Büchel BV**  
Fokkerstrat 24,  
3905 KV  
Veenendaal,  
Netherlands  
Tel: +33 (0)318 521500  
Fax: +33 (0)318 5400358

**Lako Tool and Manufacturing Inc.**  
7400 Ponderosa Road  
Perrysburg, Ohio 43552  
Tel: (419) 662-5256  
Fax: (419) 662-8225

**Lawson Hemphill**  
1658 G A R Highway  
Swansea, MA 02777  
Tel: (508) 679-5364  
Fax: (508) 679-5396  
Information@lawsonhemphill.com

**Adamel Lhomargy SARL**  
Z.A. de l'Habitat,  
Bâtiment 6 Route  
d'Ozoir, 77680  
Roissy en Brie, France  
Tel: +33 (0) 1 6440291  
Fax: +33 (0) 1 64409211

**TMI Canada**  
P.O. Box 203  
Pointe-Claire Dorval  
QC, H9R-4N9 CAN  
Tel: (514) 426-5855  
Fax: (514) 426-1557

